

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 24/38, 28/02, C09K 7/02		A1	(11) International Publication Number: WO 96/40598
			(43) International Publication Date: 19 December 1996 (19.12.96)
(21) International Application Number: PCT/US96/08049		(81) Designated States: CA, JP, NO, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 30 May 1996 (30.05.96)			
(30) Priority Data: 08/476,836 7 June 1995 (07.06.95) US		Published With international search report.	
(71) Applicant: THE NUTRASWEET COMPANY [US/US]; 1751 Lake Cook Road, Deerfield, IL 60015-5239 (US).			
(72) Inventors: SKAGGS, Bryan; 11390 Turtleback Lane, San Diego, CA 92127 (US). DIAL, Harold; 11640 Avenida Marcella, El Cajon, CA 92120 (US). RAKITSKY, Walter; 7271 Enders Avenue, San Diego, CA 92122 (US).			
(74) Agents: FITZPATRICK, Joseph, M. et al.; Fitzpatrick, Cella, Harper & Scinto, 277 Park Avenue, New York, NY 10172 (US).			
(54) Title: STABLE SUSPENSION OF HYDROCOLLOIDS AND SUPERPLASTICIZER			
(57) Abstract <p>The present invention comprises a stable hydrocolloid composition in which preferably welan gum is uniformly dispersed in a superplasticizer such as sulfonated naphthalene, sulfonated melamine, modified lignosulfate, their derivatives and mixtures thereof. The mixture is wet milled to form an extremely fine particle size distribution of the gum. The composition is rapidly hydratable and useful as a stabilizing additive in many cement and drilling fluid applications.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

STABLE SUSPENSION OF HYDROCOLLOIDS AND SUPERPLASTICIZER

5

Field of the Invention

The present invention relates generally to industrial gums and their use in cements, masonry grouts, oil field drilling fluids and the like. More specifically, the invention relates to an improved Welan gum composition and its numerous applications in this area.

10

Background of the Invention

Concretes and mortars are cement compositions additionally containing aggregate (e.g., sand and rock) and water. When water is added to the cement, this forms a paste which hardens to a solid structure. Various additives have been used in these cement compositions to modify their properties for specialized applications. For example, long fibers such as asbestos reduce the sagging of these pastes and thus is beneficial when applying tiles to a vertical surface. Freezing point depressants are used when cements are to be poured in subfreezing temperatures. Cellulosic based polymers have been used in cements to control water retention, working time, and in certain cases, the sedimentation of particles in the pastes. Bentonite clay has also been used for this purpose. Other polymers, such as the polyvinyl alcohols and methyl methacrylates, have been used to reduce friction when pumping these pastes and to otherwise modify their workability. Fumed silica is used as an additive to make stronger concrete with reduced permeability.

- 2 -

The term "cement compositions" refers to hydraulic cements such as finely ground and calcined calcium silicates and calcium aluminates which when mixed with water react to form a hard, rock-like mass. There are many well known cement compositions such as: portland cement, 5 portland pozzolan cement (containing about 15-40% pozzolan), blast furnace slag cement, slag cement (containing blast furnace slag and hydrated lime), masonry cement (e.g., adhesive mortars), construction concrete (containing sand and aggregate, oil-well cement (i.e., cements with retarders to prevent rapid setting so that they may be used at the high temperature and pressure 10 environments of deep wells), aluminous cement (containing high amounts of calcium aluminates, expansive cements (containing high sulfate and alumina concentrations and which expand on hardening), air entrained cement (containing compounds which retain air bubbles and thus yield frost- and chemical-resistant concretes), lightweight concrete (containing low 15 density materials such as furnace clinker, pumice, foamed slag, fly ash, gas, wood, etc.) heavy concrete (containing dense material such as barite, iron ore (i.e., ilmenite or hematite), steel, etc.), and low heat concrete (with modified compositions that minimize heat generation during the setting process).

20 With respect to oilfield cements, it is desirable, while drilling a subterranean well, to line the surface of the hole with hollow pipe known as casing. The casing is held in place by attaching the casing to the borehole wall with a cement slurry. The cement slurry is put in place by pumping the slurry down the inside of the casing to the bottom of the hole 25 and up the annulus between the casing and borehole wall. The cement is then allowed to set for several hours to gain strength before any other operation is commenced.

The main purposes of primary cementing are:

1. Most importantly, to allow the segregation of individual 30 formations behind the pipe so that fluids from one

- 3 -

formation cannot flow into another, i.e., the cementation of an oil/gas well. This allows for the production from a specific zone.

2. To add support for the casing by physically bracing or preventing the formation of pressure imposed on the casing.
3. To retard corrosion by minimizing contact between the casing and corrosion formation waters.

Oilfield cements are similar to those used in construction (i.e., portland cement). The American Petroleum Institute has set specifications for oilfield cements. These are classified as "A" through "H", "J" and "N", all of which the present invention is useful in.

Cement additives in oilfield cements are materials mixed in the slurry for one or more of the following purposes:

1. Reducing or increasing density;
2. Increasing volume at reduced unit cost;
3. Accelerating or retarding slurry thickening time;
4. Increasing strength;
5. Preventing loss of whole cement slurry;
6. Increasing or improving the cement's durability;
7. Decreasing water loss from the slurry;
8. Increasing or decreasing the viscosity of the cement slurry; and
9. Preventing gas migration.

The water loss of a "neat" cement slurry (cement and water only) is very high and rapid. When a slurry contacts a porous formation rock (such as an oil bearing sandstone) it may become quickly dehydrated by the water filtering into the formation. This causes the cement to "flash set." This may cause the casing to stick to the borehole before all the slurry is pumped in the annulus or before the casing is in the proper position.

Bentonite in concentrations of 0-14% (wt./wt. of dry cement) has been used in the past to control the water loss from the slurry. Cellulosic polymers such as carboxymethylhydroxyethyl cellulose (CMHEC) and hydroxyethyl cellulose (HEC) have also been used as water loss control agents and control the set of the cement at levels from about 0.2% to 0.9%.

Welan gum is an industrial grade of a bacterial polysaccharide produced by the growth of the *Alcaligenes* strain ATCC 31555 in a pure culture fermentation using carbohydrates as a carbon source. The product is recovered from the fermentation broth by precipitation with alcohol. Welan gum is a polysaccharide gum which comprises principally a heteropolysaccharide containing the neutral sugars D-glucose, D-glucuronic acid, L-rhamnose and L-mannose and glycosidically linked acetyl ester groups. The structure of this polysaccharide is described in Jansson P E, Linberg B, and Wildmalm G (1985) *Carbohydrate Research* 139, 217-223.

The rapidly hydrating welan gum composition used in the present invention is a novel combination of welan gum and a superplasticizer. U.S. Pat. No. 4,342,866, to Kang et al., describes a procedure for making welan gum and this is hereby incorporated by reference.

U.S. Pat. No. 4,981,520 to Hoskin et al., discloses a welan gum composition comprising welan gum, a phenolic resin such as resorcinol and an aldehyde. The compositions form stable gels in low salinity brines and are useful in selectively plugging highly permeable zones in a subterranean formation such as oil wells. This improves sweep efficiency during fluid flood oil recovery processes.

U.S. Pat. No. 4,963,668 to Allen et al., teaches the use of a low viscosity welan gum in cement compositions that allegedly exhibit improved workability, suspension of aggregates flow characteristics and resistance to water loss. Preferably, the range of amounts of welan gum used is from 0.1-0.5%.

- 5 -

U.S. Pat. No. 5,004,506 also to Allen et al., teaches welan gum in cement compositions as before, wherein a dispersant such as sodium citrate, sodium naphthalene sulfonates and the like, is added to reduce the viscosity of cement slurries and to serve as an aid in fluid loss control by dispersing the particles in the slurry.

U.S. Pat. No. 5,175,277 to Rakitsky et al., teaches and claims a rapidly hydratable welan gum which can be mixed with a carrier that is usually a superplasticizer, i.e., a dispersant. This is added to a dry cement/water premix and improves the cements workability, its fluid retention and prevents settling.

Finally, U.S. Pat. No. 5,290,768 teaches and claims a welan gum composition comprising welan gum and ethylene glycol. The composition displays unique viscosity and thermal properties which makes it an excellent insulation material.

None of the cited prior art however, discloses a stabilized suspension comprised of a hydrocolloid such as welan gum and a superplasticizer selected from the group consisting of sulfonated naphthalene, sulfonated melamine, modified lignosulfate, their derivatives and mixtures thereof. Moreover, none of the prior art discloses welan gum/superplasticizer compositions that are ground to an extremely fine particle size so as to afford its suspension superior viscosity and flow characteristics when used in cement, grout and oil field applications.

Summary of the Invention

The present invention comprises a stable hydrocolloid composition in which the hydrocolloid is uniformly dispersed in a superplasticizer such as sulfonated naphthalene, sulfonated melamine, modified lignosulfate, their derivatives and mixtures thereof. Suitable hydrocolloids include welan gum, hydroxypropylmethyl cellulose (HPMC), hydroxyethyl cellulose, polyvinyl alcohol (PVA) and the like. The mixture is wet milled

- 6 -

to form an extremely fine particle size distribution of the hydrocolloid. The composition is rapidly hydratable and useful as a stabilizing additive in many cement and drilling fluid applications.

5 Detailed Description of the Invention

 The present invention is comprised of a highly stabilized suspension consisting preferably of welan gum, or a similar hydrocolloid, that is uniformly dispersed in a superplasticizer. The liquid suspension provides a flowable welan gum product that hydrates rapidly and can be
10 metered and dispersed into concrete, grout and related cement formulations using standard equipment known in the art. The welan and superplasticizer are wet-milled to produce an extremely fine particle size that improves the suspensions stability, increases the gums hydration rate and is not plagued with the associated dust problems of welan gum compositions known in the
15 art.

 Previously developed suspensions of welan gum, especially at low concentrations, are not generally stable and particles settle within a brief period of time. These suspensions also possess a slower rate of hydration which is a critical factor in the preparation of cement, grout and/or concrete
20 useful in a number of applications including anti-washout compositions in oil and gas recovery operations. Moreover, it is a further object of this invention to use welan gum as a suspending agent for cement slurries. Although welan gum has been described in U.S. Pat. No. 4,342,866 to Kang et al. to be an excellent viscosifier and suspending agent in aqueous brines,
25 it was unexpected that the polymer would be compatible with and increase the suspension properties of cement slurries. Many other commercially available polymers are not compatible or functional in cement slurries. The compatibility and suspension properties of welan gum are advantageous in several oilfield and industrial applications. For example, welan gum
30 increases the workability of cement compositions, i.e., it improves the ability

- 7 -

of cement slurries to be easily placed in crowded areas such as around reinforcing bars without the formation of "bleed water" and aggregate settling. Under such conditions a stiff or "dry" concrete slurry would be extremely difficult to position but a more mobile "wet" slurry would produce a weak concrete and would allow settling of the aggregate. An additional advantage of the welan gum or other similar hydrocolloid concrete is the ability to place and set the formations without the need for vibrators.

The superplasticizer essentially functions as a delivery vehicle for the hydrocolloid such as welan gum as the combination of the two form a dry solid, stable suspension. The welan gum, by its very nature, is rapidly hydratable and is uniformly dispersed in the plasticizer. The suspension remains stable for matters even at elevated temperatures over 100°F.

Superplasticizers are known to function as high range water reducers in the cement industry and as dispersants in the oilfield recovery industry as they reduce the required water content of cement and washout compositions up to 30%. Suitable plasticizers useful in the practice of the present invention consist of sulphonated naphthalene, sulphonated melamine, modified lignosulfonate, their derivatives and mixtures thereof. Suitable derivatives include polynaphthalene sulphonate, sulphonated naphthalene formaldehyde, sulphonated melamine formaldehyde and the like. Other derivatives include the sodium salt of the sulphonated melamine formaldehyde, the sodium salt of sulphonated naphthalene formaldehyde and the calcium salt of sulphonated naphthalene formaldehyde.

The hydrocolloid and plasticizer are mixed generally in a 1:1 ratio and either alone or together with a bentonite extender are wet-milled in a milling apparatus such as a Hobart mixer or a Dyno-Mill to a uniform, extremely small particle size range of from about 3 μ m to about 500 μ m. Preferably, the hydrocolloid and plasticizer are ground into particles of from about 50 μ m to about 200 μ m.

- 8 -

The following examples are provided to more specifically set forth and teach means to prepare and utilize the hydrocolloid suspensions of the present invention. They are for illustrative purposes only however, and it is recognized that minor changes and variations can be made with respect to the components and parameters of the composition and process. To the extent that any such changes do not materially alter the final product or result they are to be considered as falling within the spirit and scope of the invention as recited by the claims that follow.

EXAMPLE 1

Two masonry grout formulations were prepared using cement components known in the art including a suspension comprised of the following. The percentages given are a weight percent basis of the total masonry grout composition.

	<u>Formulation A</u>	<u>Formulation B</u>
Welan gum	0.05%	0.1%
Welan mesh size	80	200
Kaolin	5.0%	5.0%
Polynaphthalene sulphonate	1.5%	1.5%

The suspension was produced using a high shear Hobart mixer.

The suspensions were mixed from 3.0 to 10.0 minutes to insure that the welan particles were uniformly distributed and not aggregated into clusters. The remaining grout components were then added and thoroughly mixed in a 1:1 water:grout ratio to distribute the stabilized suspension throughout the grout. Both grout compositions exhibited superior fluid loss control as measured by the Gelman Fluid loss test (10 psi for 10 min) and the higher mixing energy applied, the better the grout composition. Stability is significantly improved by reducing the welan gum particle size range and by removing any excess air from the sheared samples. Agglomerated

- 9 -

particles are more likely to plug the soil pore throats and reduce radial penetration.

EXAMPLE 2

Viscosity, fluid loss, and sedimentation of cement grouts containing blends of welan gum and HPMC (hydroxypropylmethyl cellulose) were measured to evaluate potential advantages of a blended product. The cement grouts were prepared with a Portland Type I/II cement at a 0.6 water/cement ratio with 1.14% superplasticizer based on the weight of cement (bwtc). A melamine based superplasticizer Sikament 86, was used to avoid any incompatibility problems with the cellulosic. Initial studies had been conducted to select a water/cement ratio and to determine the dose of superplasticizer required to minimize grout viscosity. The 100% welan gum and HPMC grouts contained 0.05% and 0.10% gum (bwtc), respectively. Three intermediate blend ratios were also evaluated as well as a control that contained super but no polymer.

Viscosity measurements were made on the Fann 35 (R1,B1,F1) over a shear rate range of 5 to 1000 sec^{-1} . Results for the 100% welan and HPMC grouts were as expected, with the welan gum effecting a more pseudoplastic profile compared to the cellulosic. Both grouts exhibit the same apparent viscosity at approximately 75 sec^{-1} . At less than 75 s^{-1} , the welan gum slurry is more viscous. One possible advantage to blending the gums would be an increase in the high shear rate viscosity which the HPMC could provide. This increase was found in all the blends tested.

Fluid loss measurements were made with a Gelman apparatus at 80 psid for 10 minutes. All grouts containing polymer lost 24--27% of available water compared to 48% for the control.

Sedimentation measurements were made by pouring columns of grout, allowing them to set, sectioning the column, and measuring the density. From the top of the column to the bottom, the control varied from less than 1.41 g/cc to 2.14g/cc, showing severe sedimentation. The 100%

- 10 -

HPMC grout varied from 1.62 g/cc to 2.14 g/cc compared to a very stable 1.75 g/cc to 1.77 g/cc for the 100% welan gum grout. All blends tested were very similar to the 100% welan gum grout, that is, sedimentation stability can be achieved with these blends even at relatively low welan gum concentrations.

Therefore, it is evident that blends of welan gum and HPMC can result in grouts higher high shear rate viscosities than the straight welan slurries without sacrificing sedimentation stability.

EXAMPLE 3

Stabilized welan gum anti-washout suspensions were compared with two cellulosic anti-washout formulations in terms of hydration rate, viscosity, washout, slump, slump loss and static bleed. The hydration rate T_{90} is measured as a function of the time it takes the composition to reach 90% torque using QC test procedures.

A welan gum/sulphonated melamine suspension was prepared and was added to the concrete anti-washout base in an amount of 0.15% based on the total weight of the anti-washout composition (bwtc). Hydroxypropylmethyl cellulose (HPMC) and hydroxyethyl cellulose (HEC) were similarly formulated as comparative anti-washout compositions. The following results were observed.

<u>% Washout Welan gum/sulphonated melamine at 0.15%</u>					
T90	Prehydrated	2 min.	4 min.	7 min.	13 min
Wet	3.42%	4.6%	5.5%	6.0%	8.25%
Dry			5.49%	5.32%	4.92%
<u>% Washout 15% HPMC 1.0% HEC</u>					
Wet	6.08%				
Dry	12.39%		6.59%		

The lower percentages exhibited by the welan gum/sulphonated melamine compositions indicate improved hydration which consequently indicates a composition with improved washout control.

- 11 -

CLAIMSWhat We Claim Is:

1. An improved solid stabilized suspension comprised of a rapidly hydratable hydrocolloid uniformly dispersed in a superplasticizer.
2. The stabilized suspension of claim 1 wherein said hydrocolloid is selected from the group consisting of welan gum, hydroxypropylmethyl cellulose, polyvinyl alcohol, hydroxyethyl cellulose, polyacrylamide and mixtures thereof.
3. The stabilized suspension of claim 1 wherein said hydrocolloid is welan gum.
4. The stabilized suspension of claim 3 wherein said superplasticizer is selected from the group comprising sulfonated naphthalene, sulfonated melamine, modified lignosulfate, their derivatives and mixtures thereof.
5. The stabilized suspension of claim 4 wherein said hydrocolloid and plasticizer are milled together to a particle size range of from about $3\mu\text{m}$ to about $500\mu\text{m}$.
6. The solid stabilized suspension of claim 5 further comprising bentonite, kaolin and a bentonite extender.
7. An improved masonry grout with improved bond strength, flowability and stability comprising a solid stabilized suspension consisting of a rapidly hydratable hydrocolloid uniformly dispersed in a superplasticizer.

- 12 -

8. The masonry grout of claim 7 wherein said hydrocolloid is selected from the group consisting of welan gum, hydroxypropylmethyl cellulose, hydroxyethyl cellulose, polyvinyl alcohol, polyacrylamide and mixtures thereof.

9. The masonry grout of claim 8 wherein said hydrocolloid is welan gum.

10. The masonry grout of claim 9 wherein said superplasticizer is selected from the group comprising sulfonated naphthalene, sulfonated melamine, modified lignosulfate, their derivatives and mixtures thereof.

11. The masonry grout of claim 10 wherein said welan gum and superplasticizer are particulated in a particle size range of from about $3\mu\text{m}$ to about $500\mu\text{m}$.

12. The masonry grout of claim 11 further comprising bentonite, kaolin and a bentonite extender.

13. An anti-washout composition for flushing subterranean oil formations comprising a solid stabilized suspension consisting of a rapidly hydratable hydrocolloid uniformly dispersed in a superplasticizer.

14. The anti-washout composition of claim 13 wherein said hydrocolloid is selected from the group consisting of welan gum, hydroxypropylmethyl cellulose, hydroxyethyl cellulose, polyvinyl alcohol, polyacrylamide and mixtures thereof.

15. The anti-washout composition of claim 14 wherein said hydrocolloid is welan gum.

- 13 -

16. The anti-washout composition of claim 15 wherein said superplasticizer is selected from the group comprising sulfonated naphthalene, sulfonated melamine, modified lignosulfate, their derivatives and mixtures thereof.

17. The anti-washout composition of claim 16 wherein said welan gum and plasticizer are particulated together in a particle size range of from about $3\mu\text{m}$ to about $500\mu\text{m}$.

18. The anti-washout composition of claim 17 further comprising bentonite, kaolin and a bentonite extender.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 96/08049

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C04B24/38 C04B28/02 C09K7/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C04B C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,4 217 229 (WATSON) 12 August 1980 see column 1, line 17-31 see column 5, line 7-11 Examples	1,2,4,5, 13,14, 16,17
Y		1-4, 13-16,18
X	US,A,5 804 506 (ALLEN ET AL.) 2 April 1991 cited in the application see column 3, line 23-52 see column 6, line 11 see column 6, line 30-35	1-12
Y		1-4, 6-10,12

	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another claim or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

Z document member of the same patent family

Date of the actual completion of the international search

9 September 1996

Date of mailing of the international search report

27.09.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentkan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Mini, A

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/08049

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,5 228 524 (JOHNSON ET AL.) 20 July 1993 see column 3, line 12-15; claim 8	1-5, 13-17
Y	---	1-4, 13-16,18
Y	EP,A,0 654 516 (RWE-DEA AKTIENGESELLSCHAFT FÜR MINERALÖL UND CHEMIE) 24 May 1995 see claims 1-6 -----	1-4, 6-10, 12-16,18

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Appl. No.

PCT/US 96/08849

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4217229	12-08-80	US-A- 4141843	27-02-79
		AU-B- 515554	09-04-81
		AU-B- 2447177	26-10-78
		CA-A- 1082906	05-08-80
		FR-A- 2364957	14-04-78
		GB-A- 1541759	07-03-79
		NL-A- 7703505	22-03-78
		SE-A- 7704112	21-03-78
US-A-5004506	02-04-91	US-A- 4963668	16-10-90
		AU-B- 602080	27-09-90
		AU-B- 1566488	10-11-88
		CA-A- 1322011	07-09-93
		CA-A- 1324127	09-11-93
		CN-A,B 1065259	14-10-92
		DE-A- 3877411	25-02-93
		EP-A- 0290198	09-11-88
		EP-A- 0507419	07-10-92
		IE-B- 62112	14-12-94
		JP-A- 63315547	23-12-88
		KR-B- 9601425	27-01-96
US-A-5228524	20-07-93	AU-B- 3785793	13-09-93
		NO-A- 9317217	02-09-93
EP-A-654516	24-05-95	DE-A- 4339386	24-05-95